Kivaev et al.

3,786,812

3,944,347

1/1974

3/1976

[11]

[45]

Oct. 23, 1979

[54]	COMBINE	ED CONTACT LENS
[76]	Inventors:	Anatoly A. Kivaev, ulitsa Konstantinova, 24, korpus 2, kv. 37; Vladimir A. Barkov, ulitsa Polyarnaya, 26, korpus 2, kv. 189, both of Moscow; Robert I. Ezrielev, ulitsa Ziny Portnovoi, 17, korpus 3, kv. 101; Irina A. Arbuzova, ulitsa Torzhkovskaya, 14, kv. 11, both of Leningrad, all of U.S.S.R.
[21]	Appl. No.:	639,366
[22]	Filed:	Dec. 10, 1975
[30]	Foreig	n Application Priority Data
Dec	:. 17, 1974 [SI	U] U.S.S.R 2082801
[51] [52]	Int. Cl. ² U.S. Cl	G02C 7/04 351/160 R; 264/1; 351/160 H
[58]	Field of Sea	arch 351/160-162
[56]		References Cited
	U.S. I	PATENT DOCUMENTS
3,6	88,111 1/19 19,044 11/19 28,317 4/19	71 Kamath 351/160

Neefe 351/162 X

Barkdoll et al. 351/160

FOREIGN PATENT DOCUMENTS

45857	2/1966	German Democratic Rep 351/160
2309933	9/1974	Fed. Rep. of Germany 351/160
		United Kingdom 351/160

Primary Examiner-John K. Corbin Assistant Examiner—Scott J. Sugarman

Attorney, Agent, or Firm-Lackenbach, Lilling & Siegel

[57] **ABSTRACT**

The combined contact lens is characterized in that it comprises a zone of a hydrophilic material, an aperture in the center of said zone, and a solid body from an optically transparent material fixed in said aperture, said solid body being made in the form of a rod bonded chemically with said zone.

In the method for the manufacture of the combined contact lens, a hydroxyl-containing monomer is polymerized in the presence of an agent initiating polymerization, a solvent, and a linking agent, inside a mould provided with a rod located in the center of the mould and made from a polymer that is inactive toward water but swells in the solution of the starting hydroxyl-containing monomer.

The invention provides good toleration of the lens with the patient and ensures optimum optical effect with various abnormalties of refraction and in various pathological states of the cornea.

5 Claims, 3 Drawing Figures

